

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
3 June 2004 (03.06.2004)

PCT

(10) International Publication Number
WO 2004/046254 A1

(51) International Patent Classification⁷: C09C 1/00

(21) International Application Number:
PCT/EP2003/050817

(22) International Filing Date:
12 November 2003 (12.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02406007.1 21 November 2002 (21.11.2002) EP

(71) Applicant (*for all designated States except US*): CIBA
SPECIALTY CHEMICALS HOLDING INC. [CH/CH];
Klybeckstrasse 141, CH-4057 Basel (CH).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): BUJARD, Patrice
[CH/CH]; Oberer Rebbergweg 29, CH-4153 Reinach
(CH). BUGNON, Philippe [CH/CH]; Impasse des Rosiers
4, CH-1724 Essert (CH).

(74) Common Representative: CIBA SPECIALTY CHEM-
ICALS HOLDING INC.; Patent Department, Klybeck-
strasse 141, CH-4057 Basel (CH).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR,
CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD,
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,
SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: OPTICALLY VARIABLE PIGMENTS HAVING AN ASYMMETRICAL LAYER STRUCTURE

(57) Abstract: The present invention relates to pigments whose particles have a length of from 2 μm to 5 μm , a width of from 2 μm to 2 μm and a thickness of from 50 nm to 1.5 μm and a ratio of length to thickness of at least 2:1, the particles having a core of a metallically reflecting material having two substantially parallel faces, the distance between which is the shortest axis of the core, comprising (a), optionally, on one parallel face of the core, an SiO_y layer wherein $0.95 < y \leq 2.0$, (b), on the SiO_y layer, an SiO_x layer wherein $0.03 < x \leq 0.95$, and (c), on the SiO_x layer, an SiO_z layer wherein $0.95 < z \leq 2.0$, to a method for the production thereof, and to the use thereof in paints, textiles, ink-jet printing, cosmetics, coating compositions, plastics, printing inks and in glazes for ceramics and glass. The pigments without an SiO_y layer produce brilliant colours. The pigments with an SiO_y layer are opaque and exhibit brilliant colours with a metallic appearance.

WO 2004/046254 A1